



Eco-Friendly

NON-STICK COATING

Non-Toxic

SINOGRACE

The Chemical Company

Teflon Coatings

PF-600 Water based fluororesin non-stick coating

DESCRIPTION

PF-600 is designed with two-layer coating system. Thanks to its high density, good inadhesion, easy-to-clean performance and strong practicability. It is applicable for substrates like aluminum, alloy and stainless steel etc.

TYPE

Water based fluororesin

KEY

- Eco-friendly
- Excellent heat resistant

FEATURES

- Excellent chemical resistance and abrasive resistance
- Excellent and lasting non-stick performance, easy to clean

TYPICAL

Appearance Black liquid (Primer and top)

Solid content (%) 35±1

Viscosity (cp) 600~1000 Primer
400~800 Top

Density (g/ml) 1.20 Primer/1.30 Top

pH 8-11(Primer and top)

Color of the film surface Black with metallic (Flat and smooth)

PROPERTIES

Curing temperature (°C) 380-420

Gloss (60 ° glossimeter) 10-20

Film thickness (µm) 20-30

Non-stick performance >10 cycles
Fry eggs at 170±10°C

Corrosion resistance No blister
Boling 10% salt water for 24 hours

Abrasion resistance 3KG/21cm² >3000 cycles

Hardness (ZHONGHUA pencil) >H

APPLICATION

- Aluminum, die-cast aluminum, alloy and stainless steel
- Frying pan, stock pot, baking tray, electric fry pan and inner pot of electric cooker etc.

STORAGE

- Available in 20 kg/ barrel or 30 kg/ barrel

AND

- Store products in tightly closed original containers at 5-35°C
- Shelf life: 6-9 months from delivery date

HANDLING

- According to non-dangerous goods transport

Anhui Sinograce Chemical Co., Ltd.

Tel: +86-0551-63459511

Email: sales@sinogracechem.com

Add.: Hefei city, Anhui province, China

Mob: +86 15855525589

Web: www.sinogracechem.com



Eco-Friendly

NON-STICK COATING



Non-Toxic

SINOGRACE

The Chemical Company

1. Requirement on pre-treatment

- Firstly, apply high-temperature degreasing, then wash with 1%~3% NaOH solution (60°C) for more than 6 minutes, dry it after water rinsing;
- Blast with 80#~120# corundum to make the surface roughness reach 2.0μ~3.0μ, pay attention to sandblast evenly;
- Wash with 1%~3% NaOH solution(60°C) for more than 6 minutes, rinse with water;
- Wash with 1%~3% hydrochloric acid solution (60°C) for more than 6 minutes, rinse with water and dry.

2. Preparation of the coating

- Dispersion of coating: the coating must be fully dispersed before operation;
- Viscosity adjustment: the viscosity could be adjusted according to different spray methods. Dilute with clean water if the viscosity is over high;
- Coating filtration: filtrate the coating with screen (100mesh) before using.

3. Application

- The spraying environment should be dry, well-ventilated, no smoking and fire. We suggest using dedicated spray gun, elevated tank and curing oven;
- The air compressor should be degreased, dewatered and equipped with water oil separator before using;
- Roll the coating at 30rpm speed before using to make sure there is no sediment, and filter with 100 mesh screen;
- Adjust atomization and oil pump capacity of the spraying gun; make sure the unit is clean and flat;
- Preheat the substrate to 35°C and spray the primer. Dry it at temperature of 120°C~150°C for 10min-15min. Keep the thickness of primer within 12μm-18μm;
- Spray top coating after the primer is dry and cooling to room temperature, then spray the top. Dry the unit at the temperature of 100°C~150°C for 10~20 min, and gradually increase the temperature to 380°C~420°C. Keep for 10 min. Keep the thickness of top coat within 10μm~12μm. The thickness of two coat tally should be between 20μm~30μm;
- The oven (or the tunnel drier) must be well ventilated; otherwise, it will lead to color change of coating.

HOW TO USE

Anhui Sinograce Chemical Co., Ltd.

Tel: +86-0551-63459511

Email: sales@sinogracechem.com

Add.: Hefei city, Anhui province, China

Mob: +86 15855525589

Web: www.sinogracechem.com